

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE Aug. 31, 1994		3. REPORT TYPE AND DATES COVERED Final 1 Jul 91 - 30 Jun 94
4. TITLE AND SUBTITLE  HIGH-TOUGHNESS GLASS-CERAMICS			5. FUNDING NUMBERS  D AAL03-91-G-6211	
6. AUTHOR(S)  MINORU TOMOZAWA			8. PERFORMING ORGANIZATION REPORT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Rensselaer Polytechnic Institute Materials Engineering Dept. Troy, NY 12180-3590			10. SPONSORING / MONITORING AGENCY REPORT NUMBER  ARO 28577.10-MS	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.	
12a. DISTRIBUTION / AVAILABILITY STATEMENT  Approved for public release; distribution unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Two different methods were used to prepare tough glass-ceramics containing ZrO <sub>2</sub> . One was to melt ZrO <sub>2</sub> -containing Li <sub>2</sub> O-Al <sub>2</sub> O <sub>3</sub> -SiO <sub>2</sub> glasses and transform them by controlled crystallization. The other was to sinter BaO-SiO <sub>2</sub> -Al <sub>2</sub> O <sub>3</sub> glass powder together with ZrO <sub>2</sub> powder. In both materials, some toughness improvement by the transformation of zirconia during fracture was observed. However, unexpectedly, the greater toughness improvement was realized when the zirconia particles in the glass-ceramics were transformed prior to the fracture by cooling to a lower temperature, e.g., liquid nitrogen temperature. This drastic increase of the fracture toughness was attributed to the deflection of the propagating crack by the large stress fields around the transformed (monoclinic) zirconia. The examination of the fracture surface demonstrated clearly that the crack deflection is taking place in the specimen with transformed zirconia.  DTIC QUALITY INSPECTED 4				
14. SUBJECT TERMS glass-ceramics, fracture toughness, zirconia transformation, crack deflection.			15. NUMBER OF PAGES 9	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED			16. PRICE CODE	
18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED		19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED		20. LIMITATION OF ABSTRACT UL

19950203 250

HIGH-TOUGHNESS GLASS-CERAMICS

FINAL REPORT

MINORU TOMOZAWA

August 31, 1994

U.S. ARMY RESEARCH OFFICE

GRANT NUMBER DAAL03-91-G-0211

RENSSELAER POLYTECHNIC INSTITUTE

TROY, NY 12180-3590

Accession For	
NTIS CRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification _____	
By _____	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

APPROVED FOR PUBLIC RELEASE;

DISTRIBUTION UNLIMITED.

## STATEMENT OF THE PROBLEMS STUDIED

Glasses and ceramics have many desirable characteristics such as light weight and refractoriness. But in general they lack toughness, or the ability to resist crack propagation. Tougher glass and ceramics are desired in many applications. Addition of  $\text{ZrO}_2$  at high temperature is one of the effective ways to increase the toughness of glasses and ceramics. A high temperature form of zirconia, tetragonal zirconia, transforms upon cooling at  $\sim 1000^\circ\text{C}$  to monoclinic zirconia and expands. When  $\text{ZrO}_2$  powder is dispersed in a glass or ceramic matrix, this transformation is shifted to lower temperature or suppressed until the time of fracture. Transformation during fracture reduces the crack tip tensile stress, thus making the crack propagation difficult. This mechanism of toughening, called transformation toughening, has been applied to a variety of different ceramics. Application of this toughening process to glass-ceramics has been investigated in this research program. Glass-ceramics with zirconia have been prepared by two different methods: (i) melting of glass containing zirconia and crystallizing the glass by controlled heat-treatment, (ii) glass powder is sintered together with zirconia powder and crystallized. The former is simpler in operation, but it usually requires a high temperature for glass melting, especially when the incorporation of a large amount of  $\text{ZrO}_2$  is desired. In the latter, a larger quantity of  $\text{ZrO}_2$  can be incorporated more easily but the process is more complicated and the product usually contains pores.

## SUMMARY OF THE MOST IMPORTANT RESULTS

I. Fracture Toughness of  $\text{ZrO}_2$ -containing Glass-Ceramics

## (A) Melting method.

Up to 15 wt%  $\text{ZrO}_2$  was added to the  $\text{Li}_2\text{O}-\text{Al}_2\text{O}_3-\text{SiO}_2$  system which, upon heat-treatment, produced  $\beta$ -eucryptite ( $\text{Li}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$ ) phase. While the fracture toughness was observed to increase with  $\text{ZrO}_2$  addition, primarily because of the large thermal expansion anisotropy of the  $\beta$ -eucryptite phase, extensive spontaneous cracking occurred when the grain size of this phase becomes larger than  $\sim 1 \mu\text{m}$ .

## (B) Sintering method.

A  $\text{BaO}-\text{SiO}_2-\text{Al}_2\text{O}_3$  glass which produced the best sintering characteristic was melted and pulverized. To this glass powder, various amounts of 10 vol%  $\text{CeO}_2$ -stabilized tetragonal  $\text{ZrO}_2$  powder were added and sintered. The fracture toughness increase by more than 100% was possible by choosing the grain size of tetragonal zirconia powder. Even greater increase of fracture toughness was realized by transforming tetragonal zirconia to monoclinic zirconia by cooling the specimen to liquid nitrogen temperature prior to the mechanical testing at room temperature. Selected fracture toughness results are shown below.

fracture toughness ( $\text{MPa}\sqrt{\text{m}}$ )

at room temperature

(a) $\text{BaO}-\text{SiO}_2-\text{Al}_2\text{O}_3$ glass-ceramics	$0.9 \pm 0.1$
(b) $\text{BaO}-\text{SiO}_2-\text{Al}_2\text{O}_3 + 10 \text{ vol}\% \text{ZrO}_2$	$1.8 \pm 0.3$
(c) sample (b), after cooling to liq. $\text{N}_2$	$3.0 \pm 0.6$

Apparently, several different mechanism are operating in

ZrO<sub>2</sub>-containing glass-ceramics. The following toughness processes appear to be involved.

(i) ZrO<sub>2</sub> transformation toughening.

This involves the stress-induced transformation of tetragonal ZrO<sub>2</sub> to monoclinic ZrO<sub>2</sub>. This was the originally intended mechanism.

(ii) residual stress toughening.

Thermal expansion mismatch of two phases or two directions of single phases produces residual stress. This can cause toughening in some Li<sub>2</sub>O-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> systems.

(iii) crack deflection by inclusion.

When tetragonal ZrO<sub>2</sub> transforms into monoclinic ZrO<sub>2</sub> in a glass-ceramic matrix, an extremely large stress is produced around the transformed particle. This causes crack deflection and leads to toughening.

Of particular interest in this research is the greater toughness improvement realized when the zirconia particles in the glass-ceramics transformed prior to the fracture. The accompanying figures demonstrate the crack deflection mechanism. The cooled specimens with transformed (monoclinic) zirconia exhibit tortuous path for cracks. For example, figure (a) and (b), which show the fracture surfaces, reveal a rougher surface for sample cooled to liquid nitrogen temperature. Correspondingly, figure (c) and (d), which show zirconia on the fracture surface, reveal more zirconia after cooling, even though the zirconia content remains unchanged, indicating that the cracks are deflected towards zirconia particles.

## II. Crystallization of Lithium-Disilicate Glass

In the course of crystallization study of glasses, an interesting phenomenon was observed. Usually, lithium disilicate glasses crystallize into lithium silicate,  $\text{Li}_2\text{O} \cdot 2\text{SiO}_2$  without changing composition. Some reported that metastable lithium metasilicate crystals ( $\text{Li}_2\text{O} \cdot \text{SiO}_2$ ) precipitated first and then disappeared by a longer heat-treatment. It was discovered that the lithium metasilicate crystal precipitated from lithium silicate glasses predominantly when the glass was heat-treated in a  $\text{LiNO}_3$  melt near the glass transition temperature. Apparently the lithium oxide is incorporated into the glass from the  $\text{LiNO}_3$  melt at the treatment temperature. This is contrary to the commonly accepted notion that at the glass transition temperature, only Li is mobile but not oxygen.

## List of Publications

1. "Sintering and Crystallization of BaO-SiO<sub>2</sub> System Glass-ZrO<sub>2</sub> Powder Mixtures," Srinivasan Sridharan and Minoru Tomozawa, Ceramic Trans., **30**, 363 (1993).
2. "Effect of Various Oxide Additives on Sintering of BaO-SiO<sub>2</sub> System Glass-Ceramics," S. Sridharan and M. Tomozawa, J. Mat. Sci. **27**, 6747 (1992).
3. "Glass-Ceramics as New Materials," Minoru Tomozawa and Richard D. Sarno, Chem. Express, **6**, 949 (1991).
4. "Toughening of Glass-Ceramics by both Transformable and Transformed Zirconia," S. Sridharan and M. Tomozawa, to appear in J. Non-Cryst. Solids.
5. "Crystallization of Lithium Metasilicate From Lithium Disilicate Glass," Jeffrey R. Jacquin and Minoru Tomozawa, to appear in J. Non-Cryst. Solids.
6. "Toughening of Sintered Glass-Ceramics by Zirconia," Srinivasan Sridharan, Ph.D. Thesis (1994).
7. "Crystallization of Lithium Metasilicate From Lithium Disilicate Glass," Jeffrey R. Jacquin, Master's Thesis (1994).

8. "Microstructure Development and Mechanical Properties of Lithium Aluminum Silicate-Zirconia Glass-Ceramics," Richard D. Sarno, Ph.D. Thesis (1994).
9. "Toughening Mechanisms for a Zirconia-Lithium Aluminosilicate Glass-Ceramics," Richard D. Sarno and Minoru Tomozawa, Submitted to J. Mat. Sci.

#### PARTICIPATING SCIENTIFIC PERSONNEL



Minoru Tomozawa, Principal Investigator, Professor of Materials Engineering.

Richard D. Sarno, Research Assistant, earned Ph.D. in December, 1993.



Sridharan Srinivasan, Research Assistant, earned Ph.D. in December, 1993.

Jeffrey R. Jacquin, Research Assistant, earned Master's Degree, December, 1993.





Secondary electron image of the fracture surface.  
(a) before cooling, (b) after cooling.



Energy dispersive x-ray mapping of Zr on the fracture surface.

(c) before cooling, (d) after cooling.